

DUPONT™ CORIAN® PERFORMANCE PROPERTIES

PHYSICAL PROPERTIES

Property	Test	Typical Result
Density	ASTM D792	1.7 g/cm ³
Approximate weight per square foot 6 mm (¼")		2.2 lbs.
Approximate weight per square foot 12 mm (½")		4.4 lbs.
Thermal Expansion	ASTM E228	3.9 x 10 ⁻⁵ m/m °C (2.2 x 10 ⁻⁵ in./in.°F)
Hardness - Rockwell "M" Scale	ASTM D785	>85
Hardness - Barcol Impressor	ISO 19712-2 (ASTM D2583)	56

MECHANICAL PROPERTIES

Property	Test	Typical Result
Flexural Modulus	ASTM D790	1.2 x 10 ⁶ psi
Flexural Strength		10,000 psi
Tensile Modulus	ASTM D638	1.5 x 10 ⁶ psi
Tensile Strength		6,000 psi
Tensile Elongation		0.4 % min.
Compressive strength	ASTM C365	16,000 psi

FITNESS FOR USE

Property	Test	Typical Result
Light Resistance (Xenon Arc)	ISO 19712-2	Pass
Weatherability	ASTM G155	$\Delta E_{94}^* < 5$ in 1,000 hrs.
Ball Impact Resistance: Sheets No fracture—½ lb. ball - 6mm	NEMA LD 3-3.8	36 in. (No failure at height)
Ball Impact Resistance: Sheets No fracture—½ lb. ball - 12mm		144 in. (No failure at height)
Wear and Cleanability	CSA B45.5-11/ IAPMO Z124-2011	Pass
Stain Resistance		Pass
Stain/chemical-resistance test	ISO 19712-2	Pass
Resistance to cigarette burns		Pass
Resistance to dry heat		Pass
Resistance to wet heat		Pass
Hot/cold cycle water-resistance test		Pass
Load test		Pass
Dimensional stability		Pass
Resistance to surface wear	ISO 4586-2	0.18 % wt/25 revolutions
Fungal Resistance	ASTM G21	ASTM Rating of 0, No observed growth on product at 100x power
Bacterial Resistance	ASTM G22	No observed growth on product at 100x power
Microbial Resistance	UL 2824 (ASTM D6329)	Highly resistant to mold growth
Coefficient of Friction (Slip Resistance)	ASTM C1028	0.94 - 0.95 (matte finish under dry conditions) 0.50 - 0.64 (matte finish under wet conditions)

DUPONT™ CORIAN® PERFORMANCE PROPERTIES

FITNESS FOR USE (continued)

Property	Test	Typical Result
Boiling Water Resistance	NEMA LD 3-3.5	No visible change
High Temperature Resistance	NEMA LD 3-3.6	No change
Flammability, Surface Burning Characteristics of Building Materials	NFPA 101: Life Safety Code®	Class A
Flame Spread Index Surface Burning Characteristics of Building Materials	ANSI/UL 723 (ASTM E84, NFPA 255)	Flame Spread Index (FSI) <25
Smoke Developed Index Surface Burning Characteristics of Building Materials	ANSI/UL 723 (ASTM E84, NFPA 255)	Smoke Developed Index (SDI) <25
Flame Spread Surface Burning Characteristics of Flooring, Floor Covering, and Miscellaneous Materials	CAN/ULC-S102.2	Flame Spread Value 0
Smoke Developed. Surface Burning Characteristics of Flooring, Floor Covering, and Miscellaneous Materials	CAN/ULC-S102.2	Smoke Developed Value 5

Typical results for 12 mm solid colors unless gauge is specified. Properties may vary by aesthetic. These values are not intended for engineering calculations, if precise calculations are required contact DuPont for additional information.

New York City Material Equipment Acceptance (MEA) number is 150-91-M.

Sinks and lavatories meet CSA B45.5-11/IAPMO Z124-2011, ANSI Z124.3 and ANSI Z124.6 standards for plastic sinks and lavatories.

Lavatories are in compliance with HUD Use of Materials Bulletin No. 73a (UM No. 73a) requirements. Sinks and lavatories are in compliance with the International Plumbing Code and the Uniform Plumbing Code for all 50 states of the United States. Sinks and lavatories are in compliance with the National Plumbing Code of Canada.

This information is based on technical data that E.I. du Pont de Nemours and Company and its affiliates ("DuPont") believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont's control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont's negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be deemed your acceptance of this disclaimer and any changes and the reasonableness of these standards for notice of changes.

© E.I. du Pont de Nemours and Company 2015. All rights reserved.

The DuPont Oval, DuPont™, The miracles of science®, and Corian® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company ("DuPont") or its affiliates. NFPA 101: Life Safety Code® is a registered trademark of the National Fire Protection Association, Inc. K-26829 2/15