

FASTENING TO OTHER PRODUCTS

Introduction

This fabrication bulletin addresses adhering a number of products to Corian® Solid Surface.

Overview

Designs frequently call for Corian® Solid Surface to be fastened to other materials. As Corian® Solid Surface will expand at a different rate with changes in temperature than other materials it is important to incorporate this into the design. Unless the area to be fastened is small, rigid bonding methods should be avoided. A flexible bonding method such as silicone adhesive is preferred. Making the dust noncombustible or by use of proper equipment.

A. Corian® Solid Surface to Wood/Plywood

Corian® Solid Surface can be adhered to wood or plywood. Silicone adhesive is preferred as it allows for differential movement with changes in temperature and humidity.

Clear contact adhesive may be used in limited applications where only a small area (maximum length of 12" [30 cm]) is being adhered. Clear contact adhesive cannot accommodate the movement required for larger pieces.

SILICONE

Steps to completion:

1. Clean both surfaces that are to be glued together thoroughly with clear, denatured alcohol¹.
2. If flexibility is a potential problem with the application, place dabs of silicone approximately 4" (102 mm) apart on the surface that is to be adhered.

Where flexibility is not as essential, place a bead of silicone around the perimeter of the surface to be glued to, and place an "S" pattern bead through the center.

3. Press the Corian® Solid Surface or wood into position and firmly clamp.

CLEAR CONTACT ADHESIVE

Steps to completion:

1. Sand both surfaces to be glued with medium (180 grit) sandpaper. Remove all dust.
2. Spread the clear contact adhesive over both Corian® Solid Surface and wood surfaces to be glued, making sure the adhesive is in a thin, even coat.
3. Wait until both surfaces are dry to the touch, then carefully position and clamp together.

HELPFUL HINTS

Be careful you do not damage lacquered finishes when using solvents to wipe away adhesive spills.

Many colors of Corian® Solid Surface are translucent. Any other color of contact cement than clear may be visible through the surface.

B. Corian® Solid Surface to Metal

Corian® Solid Surface can be adhered to metal. Only silicone adhesive is recommended. Silicones using an acetoxy cure chemistry release acetic acid during cure. If the metal is sensitive to acetic acid use a neutral cure silicone adhesive.

Steps to completion:

1. Be sure both surfaces are flat.
2. If metal is painted or coated, sand away this coating in the area to be adhered.
3. Clean both surfaces that are to be seamed together thoroughly with clear, denatured alcohol.
4. Place dabs of silicone (approximately 1" [25 mm] round) on one surface, approximately 12" (305 mm) apart.
5. Press the Corian® Solid Surface or metal into position and clamp firmly.
6. Where caulking is required, use a color-coordinated 100% silicone sealant.

¹Denatured alcohol is the preferred solvent for cleaning Corian® Solid Surface products. Acetone is approved for cleaning Corian® Solid Surface in regions where denatured alcohol is prohibited. Please see Corian® Solid Surface Fabrication/Installation Fundamentals – Approved Cleaning Solvents (K-25701) for more details.

C. Corian® Solid Surface to Glass

Corian® Solid Surface can be adhered to glass using a clear silicone designed for glass adhesion.

Steps to completion:

1. Clean both surfaces that are to be seamed together thoroughly with clear, denatured alcohol.
2. Place dabs of silicone (approximately 1" [25 mm] round) on the surface that is to be glued to, approximately 6" (152 mm) apart.
3. Press the Corian® Solid Surface or glass into position and clamp firmly.
4. Where caulking is required, use color-matched silicone to seal the seam.

D. Corian® Solid Surface to Unfilled Acrylic

Corian® Solid Surface can be adhered to unfilled acrylic. For small areas the acrylic may be seamed with a rigid adhesive. For larger areas silicone adhesive is required to accommodate differential expansion.

To rigidly bond acrylic to Corian® Solid Surface, use Joint Adhesive, Joint Adhesive 2.0 or clear acrylic adhesive. The clear acrylic adhesive should not be solvent based and should be compatible with cross-linked acrylics.

Steps to completion:

1. Prepare both pieces to be seamed by ensuring a perfect fit, and then lightly sand.
2. Clean both surfaces that are to be seamed together thoroughly with clear, denatured alcohol.
3. Apply a generous quantity of Joint Adhesive, Joint Adhesive 2.0 or clear acrylic adhesive to one surface.
4. Press the pieces together in position, clamp firmly and allow the adhesive to cure.
5. Trim the seam with a router, then sand to the desired finish level.

Bond larger pieces with silicone adhesive.

Steps to completion:

1. Clean both surfaces that are to be seamed together thoroughly with clear, denatured alcohol.
2. Place dabs of silicone (approximately 1" [25 mm] round) on the surface that is to be glued to, approximately 6" (152 mm) apart.
3. Press the Corian® Solid Surface or acrylic into position and clamp firmly.

HELPFUL HINTS

Do not use any glue that is solvent based.

Do not use extruded acrylic.

E. Mechanical Fasteners

Brass or plastic inserts designed for Solid Surface may be used to mechanically fasten Corian® Solid Surface to other materials. Specialty applications may have other allowable fasteners. The design must accommodate thermal expansion in the structure to which the Corian® Solid Surface is fastened as the inserts will not accommodate any movement.

The inserts should be installed according to the manufacturer's instructions.

Screws should never be inserted directly into Corian® Solid Surface.

F. Referenced Document

Corian® Solid Surface Fabrication/Installation Fundamentals – Approved Cleaning Solvents (K-25701)

PLEASE VISIT OUR WEB SITE: WWW.CORIAN.COM OR CONTACT YOUR CORIAN® REPRESENTATIVE FOR MORE INFORMATION ABOUT CORIAN® SOLID SURFACE

This information is based on technical data that DuPont Specialty Products USA, LLC and its affiliates ("DuPont") believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont's control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont's negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be deemed your acceptance of this disclaimer and any changes and the reasonableness of these standards for notice of changes.

The Corian® Solid Surface Logo and Corian® and all trademarks and service marks denoted with ™, ® or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2023 DuPont.