

COLOR FASTNESS AND EXTERIOR USE OF CORIAN® SOLID SURFACE SHEET

INTRODUCTION

This bulletin provides an overview of color performance considerations when deciding if Corian® Solid Surface sheet colors are appropriate for an exterior application. Corian® Solid Surface sheet color recommendations are based on testing performed outdoors in Florida. Preliminary assessments of new colors are made based on accelerated Atlas Ci4000 Weather-Ometer® testing performed in accordance with ASTM G155 and Florida exposure testing of comparable Corian® Solid Surface colors. The Global Corian® Solid Surface Color Portfolio contains colors that may be special order by region.

OVERVIEW

Color stability is often a primary concern when evaluating a material for exterior use, however there are other performance factors that should also be considered. Many colors of Corian® Solid Surface exhibit good color stability. All colors have low moisture absorption and resistance to stains, environmental pollutants, detergents, humidity and freeze-thaw conditions. Design flexibility, ease of fabrication, seamless appearance, thermoformability and durability make Corian® Solid Surface a versatile material. Corian® Solid Surface installations can be easily cleaned and/or sanded to restore their original appearance. Even graffiti can be removed through standard pressure washing with baking soda based cleaning agents. These performance factors combined make Corian® Solid Surface sheets an excellent choice for exterior applications.

Individual Corian® Solid Surface sheet colors change differently upon prolonged exposure to outdoor weather conditions and may exhibit color shifts which can be renewed with cleaning and/or sanding. This change is more evident in saturated, chromatic and dark colors and least evident in whites, lights and many of the earth tones. Ultimately, it is up to the end user to determine if these characteristics are acceptable for the desired application. Corian® Solid Surface sheets have been tested according to industry standards that are used in part to help determine product suitability for exterior use.

TESTING METHODS

Color assessments are made based on accelerated Weather-Ometer® testing performed in accordance with ASTM G155 testing of comparable Corian® Solid Surface colors.

Accelerated Weather-Ometer® testing artificially reproduces and accelerates weathering effects that occur from exposure to direct sunlight and rain or dew by using exposure to a xenon arc lamp and water. Color changes for both tests are measured before and after the exposure period. All exposure testing protocols are performed on nominal 12 mm (1/2") gauge product.

Corian® Solid Surface sheet colors are grouped into three performance categories. These categories are based on a projected 10-year color change performance. Color changes are measured in ΔE^*_{94} units. ΔE^*_{94} (the total color difference) and its calculation are defined in ASTM D2244. Performance categories apply only to Corian® Solid Surface sheet.

Group 1 – Color change of less than or equal to 5 ΔE^*_{94} units in 10 years – good choices for exterior applications.

Group 2 – Color change of 5 to 15 ΔE^*_{94} units in 10 years – good choices if some color change is not objectionable.

Group 3 – Color change of greater than 15 ΔE^*_{94} units in 10 years – potential choices if greater color change is acceptable.

The Global Portfolio contains colors that may not be in the standard offering in some regions. These colors have longer lead times and may have minimum order quantities.

GROUP 1

COLOR	COLOR	COLOR
Abalone	Deep Anthracite	Neutral Concrete
Antarctica	Deep Night Sky	Pebble Lane
Archeologic	Deep Nocturne	Peppered Terrazzo
Artista Beige	Deep Titanium	Rain Cloud
Artista Canvas	Designer White	Rice Paper
Artista Dust	Doeskin	River Pearl
Artista Gray	Domino Terrazzo	Sahara
Arrowroot	Dove	Salt
Ash Concrete	Dune Prima	Savannah
Aspen	Everest	Sepia Linear
Aurora	Excavage	Serene Sage
Bisque	Glacier Ice	Sparkling Granita
Bleached Nuwood	Glacier White	Sparkling White
Bone	Gray Onyx	Stonique
Cameo White	Hazelnut	Vanilla
Carrara Crema	Laguna Terrazzo	Venaro White
Carrara Lino	Light Ash	Whipped Cream
Canvas	Limestone Prima	White Jasmine
Cirrus White	Linen	White Onyx
Clam Shell	Modern White	Willow
Concrete	Neutral Aggregate	Windswept Prima

Glacier White and Designer White display exceptional color fastness properties. The projected ΔE^*_{94} is less than 2 units over 10 years.

GROUP 2

COLOR	COLOR	COLOR
Arctic Ice	Deep Sable	Sagebrush
Artista Mist	Deep Storm	Sand Storm
Artista Sage	Elegant Gray	Sandstone
Ash Aggregate	Evening Prima	Silver Birch
Calacatta Greige	Imperial Yellow	Silver Gray
Carbon Aggregate	Juniper	Silver Linear
Carbon Concrete	Lava Rock	Silverite
Cosmos Prima	Matterhorn	Sorrel
Deep Black Quartz	Natural Gray	Stonecrest Smoke
Deep Cloud	Pearl Gray	Weathered Aggregate
Deep Espresso	Platinum	Weathered Concrete
Deep Mink	Rosemary	Whisper

GROUP 3

COLOR	COLOR	COLOR
Canyon	Provence Nuwood	Smoke Drift Prima
Hot	Sandalwood	Verdant
Laguna	Silt	Witch Hazel
Nimbus Prima		

COLOR FASTNESS AND EXTERIOR USE OF CORIAN® SOLID SURFACE SHEET

REFERENCE STANDARDS

AMA 2604, Voluntary Specification, Performance Requirements and Test Procedures for High Performing Organic Coatings on Aluminium Extrusions and Panels.

ASTM B117, Standard Practice for Operating Salt Spray (Fog) Apparatus.

ASTM C666/C666M, Standard Test Method for Resistance of Concrete to Rapid Freezing and Thawing.

ASTM C756, Standard Test Method for Cleanability of Surface Finishes.

ASTM D1308, Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes.

ASTM D2244, Standard Practice for Calculation of Colour Tolerances and Colour Differences from Instrumentally Measured Colour Coordinates.

ASTM D2247, Standard Practice for Testing Water Resistance of Coatings in 100% Relative Humidity.

ASTM D2248, Standard Practice for Detergent Resistance of Organic Finishes.

ASTM D570, Standard Test Method for Water Absorption of Plastics.

ASTM G7, Standard Practice for Atmospheric Environmental Exposure Testing of Non-metallic Materials.

ASTM G21, Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi.

ASTM G85, Standard Practice for Modified Salt Spray (Fog) Testing.

ASTM G155, Standard Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials.

ISO 14021:2016, Environmental Labels and Declaration. Self-declared Environmental Claims (Type II Environmental Labelling).

ISFA-2-01 (2013), Classification and Standards for Solid Surfacing Material.

ISO 19712-2:2007, Plastics – Decorative solid surfacing materials – Part 2: Determination of properties – Sheet goods.

PLEASE VISIT OUR WEB SITE: WWW.CORIAN.COM OR CONTACT YOUR CORIAN® REPRESENTATIVE
FOR MORE INFORMATION ABOUT CORIAN® SOLID SURFACE

This information is based on technical data that DuPont Specialty Products USA, LLC and its affiliates ("DuPont") believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont's control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont's negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be deemed your acceptance of this disclaimer and any changes and the reasonableness of these standards for notice of changes..

The Corian® Solid Surface Logo and Corian® and all trademarks and service marks denoted with ™, ®, or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2024 DuPont.